

REMARKS

Entry of this amendment is respectfully requested.

This amendment is submitted to correct a translational error, as the term "actor" should be "actuator". The changes to the specification made by the amendment of January 27, 2004 are included, but not shown as underlined or strikeout as they are already entered.


Claims 4 was also amended to replace "1 wherein" with "wherein", as this was intended in the prior amendment.

No new matter has been entered by this amendment or in the substitute specification.

The Commissioner is hereby authorized to charge any deficiency in the fees filed, asserted to be filed or which should have been filed herewith (or with any paper hereafter filed in this application by this firm) to our Deposit Account No. 50-0624, under Order No. NY-DNAG-256-US. A duplicate copy of this paper is enclosed.

Respectfully submitted

FULBRIGHT & JAWORSKI L.L.P.

By 
James R. Crawford
Reg. No. 39,155

666 Fifth Avenue
New York, New York 10103
(212) 318-3148

Enclosures:
Substitute specification
Marked-up substitute specification

MARKED UP COPY OF SUBSTITUTE SPECIFICATION

INSULATION FOR PIEZOCERAMIC MULTILAYER ACTORS

FIELD OF THE INVENTION

[001] The invention relates to a method for the manufacture of piezoelectric multilayer ~~actors~~ actuators (called "actuators") hereinafter, and to an actuator ~~actor~~ manufactured by this method.

BACKGROUND AND SUMMARY OF THE INVENTION

[002] Piezoceramic multilayer actuator ~~actors~~ (see Fig. 1) in the state of the art consist of stacked thin layers of piezoelectrically active material 2, e.g., lead zirconate titanate (PZT) with conductive internal electrodes 7 arranged between them, which run alternately to the surface of the actuator ~~actor~~. External electrodes 3 and 4 connect these internal electrodes together. The internal electrodes are thereby connected electrically parallel and in a combination of two sets constituting the two terminal poles of the actuator ~~actor~~. If an electrical voltage is applied to the terminal poles it is transferred parallel to all of the internal electrodes and cause an electrical field in all layers of the active material which is thereby deformed mechanically. The sum of all these mechanical deformations is available at the end surfaces of the actuator ~~actor~~ as useful expansion 6 and/or force.

[003] Piezoceramic multilayer actuators ~~actors~~ are, in the state of the art, made in the form of monoliths, that is, the active material in the form of so-called green films are provided by screen printing methods with internal electrodes prior to sintering, pressed into actuator ~~actor~~ stacks, pyrolyzed and then sintered, resulting in the monolithic actuator ~~actor~~.

[004] A metal ground coating 3 is applied to the actuator ~~actor~~ stack 1 in the area of the brought-out internal electrodes 7, e.g., by screen printing with metal paste. This metal ground coating is strengthened by applying a metal material 4, e.g. by soldering on an embossed plate or a wire mesh. The electrical connecting wire 5 is soldered onto this strengthened coating.

[005] The structure and the manufacture of such actuators ~~actors~~ and external electrodes is thoroughly described, e.g., in DE 33 30 538 A1, DE 40 36 287 C2, US 5 281 885, US 4 845 399, US 5 406 164 and JP 07-226541 A.

[006] The spacing between the internal electrodes 2a of different polarity leading out interdigitally is so small that a flashover would take place at the surface at the working voltage. Therefore the surface is usually covered with an insulating varnish. The fact that thin varnishes offer only an insufficient protection against contact and are mechanically delicate is a disadvantage. Thick varnishes, on the other hand, tend to come loose in operation or when exposed to temperature change. The expression, interdigital areas, is to be understood to refer to the outwardly leading internal electrodes 2a in Fig. 1 between the contacted sides 3 and 4.

[007] Another possibility is to keep the electrodes from reaching all the way to the surface ("buried electrodes"), or to have only the electrodes of one polarity emerge at the surface ("half-buried electrodes"). The disadvantage is that the active surface is diminished and thus the development of the actuator's ~~actuator's~~ power is reduced. At the same time these inactive zones result in a cramping of the actuator ~~actuator~~ and are liable to crazing.

[008] Another possibility for protecting the surface is to apply a ceramic film to the green surface of the actuator ~~actuator~~, sintered them with the actuator ~~actuator~~ in order thus to achieve insulation (DE 10 021 919 A1). A disadvantage in this method is that the outside dimensions of the actuator ~~actuator~~ cannot be reproduced very accurately due to shrinkage during sintering. Moreover, this insulating layer is made relatively thick by the process (typically >50 µm) and thus has disadvantages similar to the two methods described above.

[009] The invention is addressed to the problem of achieving insulation with a ceramic which can be applied after sintering and shaping by grinding and thus can satisfy even severe geometric requirements.

[010] —This problem is solved according to the present invention, which relates to a method for the manufacture of piezoelectrical multilayer actuator ~~actuators~~, wherein thin coats of a piezoceramic material, called green leaves, are applied to the at least one internal electrode, are thus stacked one on the other in a block, that the internal electrodes are brought alternately to opposite faces of the actuator ~~actuator~~ where they are connected together by an external electrode, the actuator ~~actuator~~ green body being sintered and subject to an abrasive shaping and then the ground metallization for the external electrode is applied, characterized in that the areas to be insulated are coated by thick-layer methods with a paste consisting of an inorganic, low-sintering

material or material mixture and an organic binder system, and then are subjected to a firing process wherein the layer thickness after sintering is between 1 and 40 μm .

DETAILED DESCRIPTION

[010][011] The present invention is directed to a method for the manufacture of piezoelectrical multilayer actuators by applying thin coats of a piezoceramic material to at least one internal electrode. The internal electrodes are brought alternately to opposite faces of the actuator ~~actoe~~ where they are connected by an external electrode. The actuator ~~actoe~~ green body is then sintered and abrasively shaped. The ground metallization for the external electrode is applied. The areas to be insulated are coated by thick-layer methods with a paste made of an inorganic, low-sintering material or material mixture and an organic binder system. This is this sintered to achieve a layer thickness of between 1 and 40 microns after sintering, preferably between 2 and 20 microns and more preferably between 4 and 15 microns.

[011][012] Advantageously the coating takes place after the sintering and shaping, and the coating is fired on at temperatures between 400 and 1200°C or between 600 and 1000°C, or preferably between 650 and 850°C.

[012][013] Preferably the firing of the insulating layer takes place together with the firing on of the external electrode and forms a continuous coating.

[013][014] In an alternative embodiment, the application of the insulating coating is made after the polarization of the actuator ~~actoe~~ and, by drying at 20 to 250°C, preferably at 80 to 120°C, all electrodes of one polarity are covered, but not the electrodes of the other polarity, and thus no continuous coating is formed.

[014][015] Preferably the low-sintering material is PZT (lead-zirconate-titanate) and/or it is identical with the actuator ~~actoe~~ material.

[015][016] Advantageously, the thick coating paste consists of a glass and an organic binder system.

[016][017] Preferably the thick coating paste is applied to the green actuator ~~actoe~~ body and sintered together with the latter.

[017][018] In an advantageous embodiment the thick coating is applied by silk-screen printing, rubber-stamping or rolling or by plasma spraying.

[018][019] An actuator ~~aeter~~ which is made by the method of the invention serves advantageously for the control of an injection valve in motor vehicles.

[019][020] Additional features of the invention will appear from the figures and the embodiments which are described below.

[020][021] The surfaces to be insulated are coated by thick layer methods with a paste consisting of low-sintering PZT (known, for example, from DE 19 840 488 A1) and an organic binder system. This insulating coating is fired on at temperatures between 500 and 1200°C, preferably between 600 and 900°C.

[021][022] In another embodiment the actuator ~~aeter~~ is polarized before the screen-printed coating is applied, so that, when the paste is dried at 80-120°C pyrotension is the result. Due to electrophoretic processes this pyrotension brings the result that only every second electrode becomes coated with PZT particles. As a result, an outstanding insulation of the electrodes of different polarity is assured after sintering, without the surface being covered by a coherent layer to interfere with expansion or the development of power in the actuator ~~aeter~~.

[022][023] Examples of Preferred Embodiments

[023][024] The actuator ~~aeter~~ is constructed as usual by bringing the electrodes out interdigitally on all sides, but not on the surfaces that are to be contacted. The actuator's ~~aeter's~~ green body is sintered and can be subjected to high-precision shaping by grinding. Then the base metallization of the external electrode (making contact with electrodes of one polarity) can be applied by silk screen printing.

[024][025] Method 1: The insulating coat 8 is applied by thick layer methods together with the external electrode layers (ground metallization) and fired on together (600<TS<900°C). The insulating coat now covers all of the interdigital areas 8 of the actuator ~~aeter~~ with a coating between 2 and 20 µm, preferably 4-15 µm, thick. The latter is strongly adherent and scratch-resistant and interferes but negligibly with the stroke or power development of the

actuator aeter (Fig. 2). Then the external electrode is soldered to a screen 9 and further contacted 10. Figure 2 shows an actuator aeter with external electrodes, insulated by screen printing (full-surface).

[025][026] Method 2: The external electrode (ground metallization) is fired. The actuator aeter is then polarized and on the surfaces, which have an interdigital structure, a paste is applied, consisting of low-sintering PZT and an organic binder system. When the paste is dried at 20-250°C, due to the pyroelectric effect of the ferroelectric ceramic, an electric field is produced in the still not dried paste. Consequently, electrophoretic processes occur in the paste, so that only every second internal electrode is covered (electrodes of one polarity (Fig. 3, No. 12). The electrodes 11 of the other polarity are not covered. A subsequent firing process at temperatures around 750°C results in an adherent and scratch-resistant insulation (Fig. 3). Figure 3 shows the insulating surface of an actuator aeter with internal electrodes 11 and insulation 12 of every second internal electrode by silk-screen printing (interrupted).

ABSTRACT

The invention relates to a method for the manufacture of piezoelectric multilayer actuator ~~acters~~ in which thin layers of a piezoceramic material, called "green leaves" on which at least one internal electrode is applied, are stacked to form a block such that the internal electrodes are guided in alternation to oppositely lying surfaces of the actuator ~~actex~~, where they become bound together by an external electrode, the actuator ~~actex~~ compact being sintered and subjected to abrasive shaping, and then the base metallization is applied for the external electrode.

In order to achieve insulation with a ceramic layer which can be applied after the sintering and the abrasive shaping, and thus satisfy even stringent requirements, it is proposed that areas to be insulated be coated by thick-layer methods with a paste consisting of an inorganic, low-sintering material or a mixture of materials and an organic binder system, and be then subjected to a burning-on process, the coating thickness after the sintering being between 1 and 40 μm , preferably between 2 and 20 μm , or between 4 and 15 μm .